



PRODUCT DESCRIPTION		
Color Index	Pigment Yellow 139	
C.I. No.	56298	
Chemical Type	Isoindoline	
CAS No.	36888-99-0	
Hue Angle	72.1	DIN EN ISO 53235

PHYSICAL DATA		
Appearance	Yellow Powder	
Density [g/cm ³]	1.56	DIN EN ISO 787-10
Bulk Volume [ltr/kg]	4.07	DIN 53194
Specific Surface [m ² /g]	34	DIN EN ISO 66132

FASTNESS PROPERTIES		
Acid	4-5	DIN EN ISO 787-14
Alkali	4-5	DIN EN ISO 787-14
Migration	4-5	DIN EN ISO 14469-4
Light Fastness	7	DIN EN ISO 105-B01
Heat Resistance [°C]	240	DIN EN ISO 12877-2
Warping in HDPE	Low	DIN EN ISO 294-4

REGULATIONS	
Germany BfR recom. IX	compliant
APME AP 89/1	compliant
USA (FDA) 21 CFR § 178.3297	- -
Toys Europe EN 71-3	compliant
Toys USA ASTM F 94/62	compliant
CONEG, EC 94/62	compliant
ROHS, 2002/95/E, 2005/618/EC	compliant
End of Life Vehicles, 2000/53/EC, 2002/525/EC	compliant



APPLICATION PROFILE	
PE	recommended
PP	recommended
PP Fibre	potential use
PVC-u	recommended
PVC-p	recommended
PS	potential use
ABS	potential use
PA	-
PC	potential use
Rubber	-

STANDARD PACKAGING
- 20kg Cardboard Boxes
- Different types of packaging are available on request

® = Registered trademark of Heubach Colour Pvt. Ltd. Our product specifications and application information are based on our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and us.