

# HEUCOPHOS® ZCP-PLUS

In phenolic modified short oil alkyd



Solvent based

Heubach formulation No. 14401

08/14

FUNCTION	PRODUCT	PRODUCER	PBW
Phenolic modified short oil alkyd	WorléeKyd L 138/60X	Worlée	34.60
Solvent	Solvesso 100	Exxon	22.10
Glycol ether	Dowanol PM	CG Chemikalien	2.00
Antisettling agent	Aerosil 300	Evonik	0.30
<b>Premix.</b>			
Aromatic hydrocarbon	Xylene		2.61
Rheology modifier	Bentone 38	Elementis	0.30
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.09
<b>Mix until uniform paste prior to addition.</b>			
Drier	Octa-Soligen Calcium 10	OMG	0.45
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	9.45
Titanium dioxide	Kronos 2190	Kronos	4.50
Mica/Quartz/Chlorite	Plastorit M	Luzenac	4.50
Iron oxide black	Bayferrox 318	Lanxess	0.45
Magnesium silicate	Finntalc M15	Mondo Minerals	10.80
Magnesium calcium carbonate	Microdol Extra	Mondo Minerals	7.20
<b>Grind with a bead mill.</b>			
Drier	Octa-Soligen Cobalt 6	OMG	0.20
Drier	Octa-Soligen Zirkonium 12	OMG	0.15
Antiskinning agent	Exkin 2	Elementis	0.30
<b>Add while mixing.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.6
PVC in %			39.5

# HEUCOPHOS<sup>®</sup> ZCP-PLUS

In phenolic modified short oil alkyd



*Solvent based*

Heubach formulation No. 14401

08/14

## SPECIFICATIONS

PVC / CPVC

0.8

Solids in %

57.7

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.